DOE/ER-0046/15

J. SCOTT (281)
4-13-84

APR 1 C 1984

# Damage Analysis and Fundamental Studies

Quarterly Progress Report
July-September 1983

November 1983

U.S. Department of Energy
Office of Energy Research
Office of Fusion Energy
Washington, DC 20545

CONTENTS

Page

Foreword iii

CHAPTER 1: IRRADIATION TEST FACILITIES 1

1. RTNS-II Irradiations and Operations (LLNL) 2

*Irradiations were performed for 12 different experimenters during this quarter. Ion source development and upgrading of the extraction power supply is in progress on the right machine.*

CHAPTER 2: DOSIMETRY AND DAMAGE PARAMETERS 4

1. Fission Reactor Dosimetry - HFIR-T2, RB1 (ANL) 5

*Activation measurements, neutron fluences, and calculated damage parameters are reported for the T2 and RB1 irradiations in HFIR. Spectral differences are noted for the target (T2) and removable Be (RB1) positions when compared to previous results in the PTP position. Analysis is in progress for the T1 and CTR31 irradiations in HFIR and the MFE4B run in ORR.*

2. Experiments at the IPNS Spallation Neutron Source (ANL) 10

*Dosimetry measurements and damage calculations are reported for a cryogenic (4°K) irradiation of copper stabilizer materials at the IPNS on March 25 - April 5, 1983. The neutron fluence was 7.1 x $10^{17}$ n/cm$^2$ producing a total dose in copper of 1.6 x $10^7$ rads.*

3. A Comparison of Measured and Calculated Helium Production in Nickel for Fission Reactor Irradiations (RIES and ANL) 12

*Helium generation measurements and calculations have been performed for 45 nickel samples from 9 different fission reactor irradiations. The calculations are based on dosimetry-adjusted neutron spectra and newly evaluated cross sections for $^{59}$Ni. The measurements and calculations agree to within ±10%.*

4. 14-MeV Neutron Irradiation of Copper Alloys (U. of Wisconsin) 17

*Resistivity and Vickers microhardness measurements on copper and three copper alloys (Cu + 5%Al, Cu + 5%Mn, Cu + 5%Ni) irradiated at room temperature with 14-MeV neutrons to a maximum fluence of 3 x $10^{21}$ n/m$^2$ yield similar defect cluster densities. The defect cluster density appears to scale linearly with the square root of neutron fluence. About 16% of the Frenkel defects initially created in the cascade escape correlated recombination events.*

Page

5. 14-MeV Neutron Radiation-Induced Microhardness Changes in Copper Alloys (U. of Wisconsin1 26

*Vickers microhardness measurements with 5-g and 10-g loads were performed on copper and copper alloy (Cu-5% Al, Cu-5% Mn, Cu-5% Nil TEM disks irradiated at 25°C with 14-MeV neutrons in incrementa2 doses up to a maximum fluence of 2.2 X $10^{21}$ n/$m^2$. The change in microhardness scales linearly with the fourth root of neutron fluence following an incubation fluence, which is largest for pure Cu. The 5-g microhardness data show surface effects.*

CHAPTER 3. REDUCED ACTIVATION MATERIALS 39

1. A Comparison of Activation in STARFIRE and MARS First Walls (HEDL) 40

*Comparison activation calculations were performed for N, Al, Ni, Mo, Cu, Nb, and Pb in the STARFIRE and MARS first-wall positions. In the harder MARS spectrum the allowable limits for NRC near-surface disposal of Ni, Mo and Nb are two to five times larger than in STARFIRE.*

CHAPTER 4. FUNDAMENTAL MECHANICAL BEHAVIOR 44

1. The Micromechanical Mechanisms of Cleavage Fracture in Martensitic Stainless Steels (U. of California) 45

*Coupled measurements of tensile and blunt and sharp notch fracture properties on HT-9 show that cleavage fracture is controlled by a critical stress-critical distance criterion. The micro-cleavage fracture stress is 2400 MPa, which is consistent with the observed martensite lath packet size; and the critical distance is ~50 μm, which is consistent with observed prior austenite grain size.*

2. A Model for In-Reactor Stress Rupture of Austenitic Stainless Steels (U. of California) 52

*A model for in-reactor stress rupture of austenitic stainless steels is proposed based on stress-induced creep cavity formation on a fraction of an evolving distribution of heliwn bubbles. The model is calibrated to high temperature in-reactor data and extrapolated to lower temperatures where irradiation creep is dominant; relatively high ductilities in breeder spectra are predicted due to delocalization of microstructurally insensitive irradiation creep strains.*

Page

3. Correlation of Fracture Toughness with Tensile Properties for Irradiated 20% CW 316 Stainless Steel (HEDL and U. of Wisconsin) 60

*A modified version of the Krafft correlation was successfully employed to estimate the fracture toughness of irradiated AISI 316 using more easily obtained tensile data. It appears that fracture toughness saturates with neutron exposure at ~400°C and is sensitive to both irradiation temperature and test temperature.*

4. The Dependence on Neutron-Induced Displacement Rate of Tensile Property Changes in Annealed AISI 304 and 316 (HEDL) 66

*Tensile tests show that hardening of AISI 304 is sensitive to the displacement rate while hardening of AISI 316 is not; however, the microstructures of both are influenced by displacement rate. Insensitivity in the hardening of AISI 316 to displacement rate arises because the strengthening contribution from precipitates increases with displacement rate, whereas the strengthening contribution from voids decreases.*

5. Shear Punch Tests for Mechanical Property Measurements in TEM Disc-Sized Specimens (U. of California) 76

*This test is based on driving a cylindrical punch through a clamped specimen, and instrumenting the punch to obtain a load-displacement curve of the punching process. A number of correlations have been developed between features of the load-displacement curve and yield strength, ultimate tensile strength, work-hardening exponent and reduction in area.*

CHAPTER 5. CORRELATION METHODOLOGY 81

1. A Theoretical Assessment of the Effect of Microchemical. Microstructural and Environmental Mechanisms on Swelling Incubation in Austenitic Stainless Steels (U. of California) 82

*A critical-sized helium bubble-to-void conversion model is used to evaluate the influence of helium partitioning, sink strength, surface energy, and diffusion rates that mediate microchemical, microstructural, and environmental effects. While microchemical effects are important, they were not found to be dominant in all cases. The results suggest that unless fine distributions of helium can be maintained, swelling will be higher in fusion than in either fast- or mixed-spectrum fission environments.*

Page

2. Factors That Determine the Swelling Behavior of Austenitic Stainless Steels (HEDL and U. of Wisconsin) 89

*Once void nucleation subsides, the swelling rate of many austenitic alloys becomes rather insensitive to variables that control the transient regime of swelling. Models are presented that describe the roles of nickel, chromium, and silicon in void nucleation. The relative insensitivity of "steady-state" swelling to temperature, displacement rate, and composition is also discussed.*

3. The Lithium Shell Effect and Its Impact on Microscopy Determinations of Swelling Behavior (HEDL and U. of Missouri) 96

*The heterogeneity of swelling in some irradiated alloys arises from localized enhancement of void nucleation by the "lithium shell effect" near boron-rich precipitates. These lithium-affected volumes can be discounted in microscopy determinations of the bulk-averaged swelling rate.*

4. Conditions for the Suppression of Void Formation During Ion-Bombardment (U. of Wisconsin) 101

*In the region of ion deposition, void formation can be suppressed because the number of interstitials is larger than the number of vacancies produced by displacement damage. Void-free zones can be produced both behind and in front of the displacement damage peak. The suppression of void formation is particularly severe in low-energy ion bombardments.*

5. Correlation of Helium Content and Microstructure to Bubble Growth in Helium-Irradiated Thin Films of Nickel (U. of Virginia) 107

*Thin PVD nickel films were irradiated at 80 keV by monoenergetic helium ions to fluences as high as $10^{22}$ $m^{-2}$. Low-irradiation temperature specimens had no visible bubbles and showed a saturation level of retained heliwn. High-temperature specimens showed higher helium retention.*

6. Thermal Creep and Stress-Affected Precipitation of 20% Cold-Worked 316 Stainless Steel (HEDL) 114

*Measurements of the thermal creep of 20% cold-worked 316 stainless steel were performed for temperatures from 593 to 760°C, stress levels as high as 138 MPa, and exposure times as long as 15,000 hours. The creep strains exhibit a complex behavior arising from the combined action of true creep and stress-affected precipitation of intermetallic phases. The latter process is suspected to be altered by neutron irradiation.*

Page

7. The Influence of Irradiation and Thermal Creep on Stress Redistribution in Fusion Blankets (U. of California] 120

*The recently developed STAIRE code was used to assess the global impact (3-dimensional) of both irradiation and thermal creep strains on the stresses in a MARS blanket module resulting from thermal and swelling strains. The analyzed blanket consists of semi-toroidal tubes around the plasma. Thus, pipes of hollow circular cross sections are treated as beams hanging between the inlet and outlet headers under a variety of boundary conditions.*

8. Irradiated Behavior of High-Strength Copper Alloys (U. of Wisconsin] 127

*This report describes the initial efforts of a program designed to investigate the irradiation properties of two comnercial high-strength, high-electrical conductivity copper alloys. Resistivity and microhardness measurements were performed on as-received AMZIRC and AMAX-MZC copper alloys, and 14-MeV Cu ion irradiations were completed on 8 samples at temperatures between 300°C and 700°C (0.4 - 0.7 $T_M$) at calculated peak damage levels between 4 and 40 dpa. The correlated yield strength of the unirradiated alloys, as obtained from microhardness measurements, agrees well with values supplied by the manufacturer, but the measured electrical conductivities are significantly less than the manufacturer's values.*