



---

# **Damage Analysis and Fundamental Studies**

**Quarterly Progress Report  
October-December 1983**

---

**February 1984**

---

**U.S. Department of Energy  
Office of Energy Research  
Office of Fusion Energy  
Washington, DC 20545**

## CONTENTS

	<u>Page</u>
Foreword	iii
CHAPTER 1:        IRRADIATION TEST FACILITIES	1
1. <u>RTNS-II Irradiations and Operations (LLNL)</u>	2
<i>Irradiations were performed for 13 different experimenters during this quarter. The 50-cm targets are now in use on both the right and left machines. The extraction power supply upgrade for the left and right machines was completed.</i>	
CHAPTER 2:        DOSIMETRY AND DAMAGE PARAMETERS	4
1. <u>Fission Reactor Dosimetry - HFIR-T1, CTR39 (ANL)</u>	5
<i>Dosimetry measurements and damage calculations are reported for the T1 and CTR39 irradiations in HFIR. The T1 experiment had a maximum fluence of <math>1.47 \times 10^{23}</math> n/cm<sup>2</sup> with 29 dpa and 2291 appm He in 316 SS, while CTR39 had <math>5.32 \times 10^{22}</math> n/cm<sup>2</sup> with 13 dpa and 617 appm He in 316 SS.</i>	
2. <u>Helium Production Cross Sections for 14.8-MeV Neutrons (RI-ESG)</u>	9
<i>Total helium production cross-section measurements have been completed for the elements Be, O, Cr, and Mn, based on samples irradiated in the 14.8-MeV T(d,n) neutron spectrum of RTNS-II.</i>	
3. <u>TKIO-1 Tritium Breeding Experiment in ORR (ANL)</u>	12
<i>The TRIO-1 solid breeder (LiAlO<sub>2</sub>) tritium experiment has been completed in ORR. Tritium was extracted by a helium purge stream and counted on-line, providing a time- and temperature-dependent profile of tritium release. These tritium measurements and the dosimetry-based tritium calculations are in excellent agreement with a total tritium generation of 35.1 Ci, corresponding to a <sup>6</sup>Li burnup of 33% (0.18% of total lithium).</i>	
CHAPTER 3:        REDUCED ACTIVATION MATERIALS	16
1. <u>Reduced Activation Activities (HEDL)</u>	17
<i>Four reduced activation alloy classes, two austenitic and two ferritic, have been incorporated into the MOTA-1B experiment in the FFTF reactor to provide an early assessment of the suitability of such alloys for fusion reactor service.</i>	

## CONTENTS (Cont'd)

	Page
CHAPTER 4: FUNDAMENTAL MECHANICAL BEHAVIOR	19
1. <u>Sub-critical Crack Growth in HT9 (PNL)</u>	20
<i>Sub-critical crack growth measurements have been made on HT9 at 25°C in a 1 N H<sub>2</sub>SO<sub>4</sub> solution with the sample held at a cathodic potential of -600 mV (SCE). The tensile ductility of HT9 has previously been shown to be a minimum at -600 mV (SCE). The sub-critical crack growth behavior of HT9 was similar for material in the tempered (760°C/2.5 h) or tempered + segregated (540°C/240 h) conditions. A rising load fracture threshold of 20 MPa√m and a decreasing load fracture threshold of 65 MPa√m was measured. A rising load fracture toughness of 110√m was determined from extrapolation of the stage III crack growth curve. A K independent stage II was observed, and a stage II crack growth rate of 0.5 to 1 x 10<sup>-5</sup> mm/s was measured.</i>	
2. <u>Critical Leak Rate Flaw Sizes for Water of Lithium-Cooled Fusion Reactors (PNL)</u>	30
<i>Results suggest that the critical leak rate flaw size for helium and water are the smallest flaws that may affect reactor performance and that the threshold for subcritical crack growth in fatigue is a critical material property. Creep processes are shown to have a significant effect on the critical leak rate flaw size.</i>	
CHAPTER 5: CORRELATION METHODOLOGY	37
1. <u>Swelling of Fe-Ni-Cr Ternary Alloys at High Exposure (HEDL)</u>	38
<i>Acquisition of higher fluence data (70-110 dpa) on the swelling of austenitic Fe-Ni-Cr ternary alloys confirms the conclusion drawn earlier that the eventual swelling rate of all austenitic Fe-Ni-Cr alloys in EBR-II is ~1%/dpa in the range 400-650°C. The influence of composition and temperature lies only in the duration of the transient regime of swelling. At temperatures below 500°C, saturation of swelling appears to be occurring, often at very high swelling levels. The saturation level decreases with decreasing temperature, increasing nickel level and decreasing chromium content.</i>	

CONTENTS (Cont'd)

	<u>Page</u>
2. <u>Transmutation of Manganese-Substituted Steels in STARFIRE (HEDL)</u>	46
<i>The transmutations calculated for a STARFIRE first wall employing the manganese substitution alloys currently under investigation in the DAFS program are not expected to alter the phase stability of these alloys.</i>	
3. <u>Recent Insights on the Swelling and Creep of Irradiated Austenitic Alloys (HEDL)</u>	49
<i>It appears that all austenitic Fe-Ni-Cr alloys eventually swell during neutron irradiation at a rate of <math>\sim 1\%/dpa</math> over a surprisingly large range of temperature. In addition, there is no evidence that saturation of swelling will occur in commercial alloys at engineering-relevant levels. The sensitivities of swelling to variations in composition, fabrication, and environment lie almost exclusively in the duration of the transient regime of swelling. Irradiation creep rates at high exposures are also expected to exhibit a similar parametric insensitivity, largely because the major creep contribution appears to be proportional to the swelling rate.</i>	
4. <u>Swelling of AISI 304L in Response to Simultaneous Variations in Stress and Displacement Rate (ANL-HEDL)</u>	62
<i>The duration of the transient regime of neutron-induced swelling in annealed AISI 304L at 400°C is sensitive to both stress and displacement rate variations. However, the duration cannot be reduced below an exposure of <math>\sim 10</math> dpa, which has been found to be characteristic of all Fe-Ni-Cr austenitic alloys. This is four times larger than that currently assumed in the stress-affected swelling equation for 20% cold-worked AISI 316.</i>	
5. <u>Simple Polynomial Expressions for the Helium Equation of State (U. Wisc)</u>	68
<i>The compressibility factor <math>z = pV/NkT</math> for gaseous and solid helium has been fitted to expressions of the form <math>z = A + Bx + Cx^2 + Dx^3</math>, where <math>x</math> is the density, and the coefficients A through D are functions of temperature.</i>	