DOE/ER-0046/18

Damage Analysis and Fundamental Studies

Quarterly Progess Report
April-June 1984

August 1984

U.S. Department of Energy
Office of Energy Research
Office of Fusion Energy
Washington, DC 20545

CONTENTS

Foreword iii

CHAPTER 1: IRRADIATION TEST FACILITIES

1. RTNS-II Irradiations and Operations (LLNL) 2

Irradiations were performed on 10 different experiments during this quarter. Ion source development continues. A redesigned ground electrode assembly was installed.

CHAPTER 2: DOSIMETRY AND DAMAGE PARAMETERS

1. Dosimetry Measurements and Damage Calculations for the ORR-MFE48 Experiment (ANL) 5

After 424 full-power days, the maximum fluence in this spectral tailoring experiment was 1.9 x 10^{22} n/cm^2 producing 64 appm helium and 5.1 dpa in 316 stainless steel.

2. Measurement of Cu Spallation Cross Sections at IPNS (ANL) 11

Spallation cross sections for 21 radioisotopes of Cu have been measured at the IPNS over an energy range of 26-450 MeV.

3. Helium Generation Measurements for Ti and Cu from ORR (RI) 18

The results of helium generation measurements on Ti and Cu irradiated in the Oak Ridge Research Reactor are significantly different from predictions based on ENDF/B-V cross-section evaluations.

CHAPTER 3: REDUCED ACTIVATION MATERIALS

1. Activation of Several Oxides (HEDL) 22

The activation of MgO, BeO, Y_2O_3, Al_2O_3, and CaO was estimated for a 10 MW-yr/m^2 irradiation at a STARFIRE first-wall position. At the concentrations used for dispersion hardening, none of the oxides would, in themselves, cause an alloy to exceed shallow burial limits.

2. The Effects of Substitutional Alloying Elements in an Fe-10Cr Ferritic Alloy (HEDL) 26

In order to determine the effect of minor reduced activation element additions on microstructural development due to fast neutron irradiation, a series of 12 alloys has been prepared for irradiation in MOTA-1C. The alloy series involves additions (M) of Si, Mn, V, W, Ta, and Zr to form alloys of Fe-10Cr-0.1M and Fe-10Cr-1M.

CHAPTER 4. FUNDAMENTAL MECHANICAL BEHAVIOR

1. Relating Bubble Size to the Failure Mode of Neutron- and Helium-Irradiated Austenitic Stainless Steel (U. VA.) 30

Helium-irradiated type 316 microtensile specimens containing tiny bubbles were tensile tested at 250°C and 450°C under rapid and slow strain rates. Mixed mode failure occurred under all conditions suggesting strain rate insensitive microstructures are possible.

CONTENTS (Cont'd)

Page

2. Fundamental Flow and Fracture Studies of HT-9 (UCSB) 35

Microstructure-property-property relationships dictating lower shelf toughness of HT-9, and procedures for estimating fracture loads, have been studied. Results support a critical stress-critical distance model for cleavage fracture. A two-parameter approach is shown to be a reasonable basis for predicting fracture loads in bend specimens, and ductility studies indicate deflectional displacements of 1-2 cmlm will be the limit for thin walls containing shallow surface cracks.

3. Some Considerations of Radiation Effects on Stress Corrosion Cracking of Fusion Reactor Materials (PNL) 61

Radiolysis is not expected to increase the corrosion rate of fusion reactor materials by more than a factor of 3; however, hydrogen uptake could increase significantly in ferritic, refractory and reactive alloys. Irradiation-enhanced creep can significantly increase intergranular stress corrosion cracking, IGSCC, at stresses below the yield strength. Radiation-induced phosphorus segregation could dominate all other IGSCC effects. Calculated K_{IC} and K_{TH} results for HT-9 were reviewed; the former is low compared with experiment.

4. Strength and Microstructure in Vanadium Irradiated with T(d,n) Neutrons at 300K, 475K, and 675K (PNL) 71

Radiation strengthening was independent of irradiation temperature from 300K to 475K but decreased following irradiation at 675K. Extremely small defect clusterslloops were responsible for strengthening the 300K samples while a<100> type dislocation loops were the predominant strengthening defect at 475K. Irradiation at 675K produced heterogeneous distributions of dislocation loops and planar precipitates which prevented definite correlations between strength and microstructures from being made.

CHAPTER 5: CORRELATION METHODOLOGY

1. Correlation of Irradiated 20% CW 316 Stainless Steel Fracture Toughness with Test Temperature (HEDL) 82

A three parameter function was developed to correlate fracture toughness (J_{IC}) in 20% CW 316 SS with test temperature. The equation is applicable for the exposure range 40 to 60 dpa, irradiation temperature range 643 to 680°K, and test temperature range 293 to 923°K.

2. A Comparison of Depth-Dependent Microstructures of Ion-Irradiated 316-Type Stainless Steels (U. of Wisconsin) 86

The microstructural response of P7, a high-swelling, "pure" 316-type stainless steel, and the MFE heat of 316 stainless steel were investigated after 14-MeV Ni-ion irradiation to fluences of 3.3 x 10^{16} ions/cm^2. A 500°C irradiation of P7 produced a depth-dependent void distribution influenced by the excess interstitial effect of the bombarding ions. A 650°C irradiation of P7 produced a bi-modal void distribution at the damage peak. A 650°C irradiation of 316 SS produced needle-like precipitation in the entire damage region.

CONTENTS (Cont'd)

Page

3. Microsegregation Observed in Fe-35.5Ni-7.5Cr Irradiated in EBR-II (HEOL) 98

Annealed Fe-Ni-Cr alloys near the Invar compositional range do not appear to be in the true equilibrium state. Radiation by neutrons or charged particles accelerates the evolution toward stability, causing a spinodal-like decomposition which yields compositional micro-oscillations, densification, and a loss of both the swelling resistance and the anomalous Invar properties.

4. Experimental Investiqation of the Effect of Injected Interstitials on Void Formation (U. of Wisconsin) 107

Pure nickel, a "pure" 316 stainless steel (P7) and two high strength copper alloys have been irradiated with either 14-MeV nickel or copper ions to a peak damage level of 50 dpa (K = 0.8). The injected interstitial effect in Ni and P7 shows good qualitative agreement with nucleation theory. A copper alloy irradiated at 300°(showed a small heterogeneous void density, while no voids formed above 400°C; this result is in excellent agreement with nucleation theory.

5. The Effect of Void Surface Motion on the Void Sink Strength for Point Defects (UK-AERE, UCLA) 122

By a generalization of an analysis due to Frank of the growing precipitate, an analytic sink strength is derived for the growing void that takes account of the void surface motion in a self-consistent fashion.

6. Preparation of Ion-Irradiated Foils for Cross-Section Analysis (U. of Wisconsin-Madison) 133

A simple, routine method of general applicability has been developed for examining ion-irradiated foils in cross section. The method has been successfully demonstrated on stainless steel, a low-chromium steel, and some high-strength copper alloys.

CHAPTER 6. FUNDAMENTAL STUDIES OF SPECIAL PURPOSE MATERIALS

1. Microstructures and Physical Properties of Cu-Zr and Cu-Cr-Zr-Mg Alloys (U. of Wisconsin) 143

The 20°C electrical conductivity of as-received AMZIRC and AMAX-MZC alloys steadily increases with annealing temperatures between 300 and 550°C. The maximum conductivity is about 90% IACS for MZC and about 100% IACS for AMZIRC. AMZIRC contains incoherent Cu-Zr precipitates which are preferentially located at grain boundaries. AMAX-MZC contains the same Cu-Zr precipitates and also coherent Cr precipitates which are uniformly distributed throughout the matrix.

2. Microstructure of High-Strength, High-Conductivity Copper Alloys Irradiated at Low Temperatures (U. of Wisconsin) 149

Both AMZIRC and AMAX-MZC alloys exhibit radiation-enhanced recovery and partial recrystallization at all temperatures following ion irradiation to a peak damage level of 15 dpa (K = 0.3) at temperatures of 100 - 250°C. There is no observable void formation at temperatures of 100 - 550°C.