



Damage Analysis and Fundamental Studies

Quarterly **Progress** Report
January-March 1985

May 1985

U.S. Department of Energy
Office of Energy Research
Office of Fusion Energy
Washington, DC 20545
B&R NO. AT-1502-03-04

CONTENTS

	<u>Page</u>
Foreword	1
CHAPTER 1: IRRADIATION TEST FACILITIES	1
1. <u>RTNS-II IRRADIATIONS AND OPERATIONS (LLNL)</u>	2
<p>Irradiations were performed on 13 different experiments during this quarter. Target vacuum system modifications were completed on the right and left machines. The target chilled water system upgrade was complete.</p>	
CHAPTER 2: DOSIMETRY AND DAMAGE PARAMETERS	4
1. <u>FISSION REACTOR DOSIMETRY - HFIR-CTR 30, 36, 46 (ANL)</u>	5
<p>Dosimetry measurements and damage calculations are reported for the CTR 30, 36, and 46 experiments in HFIR. CTR 30 has the highest exposure to date with a fluence of $1.95 \times 10^{23} \text{ n/cm}^2$ producing 44 dpa and 2613 appm helium in a 316 stainless steel.</p>	
2. <u>ANALYSIS OF DAMAGE EXPOSURE RATES IN THE MATERIALS OPEN TEST ASSEMBLY OF THE FAST FLUX TEST FACILITY (HEDL)</u>	10
<p>The axial distribution of dpa/sec in stainless steel (Fe18Cr10Ni) and flux $E > 0 \text{ MeV}$ and $E > 0.1 \text{ MeV}$ were determined from the analysis of dosimetry measurements made during MOTA Cycles 1A and 1B.</p>	
3. <u>ACTIVATION CROSS-SECTION MEASUREMENTS AT RTNS-II (ANL, LLNL, RI)</u>	15
<p>Cross sections are reported for 22 reactions measured at RTNS-II in the angular range from 0-60° for neutron energies between 14.5-14.9 MeV. Results are compared to ENOFIB-V and other data.</p>	
4. <u>ISOTOPIC TAILORING WITH NICKEL-59 TO ENHANCE HELIUM PRODUCTION IN FISSION REACTOR IRRADIATIONS (HEDL)</u>	19
<p>Three heats of austenitic steel doped with Ni-59 have been prepared for irradiation in out-of-core locations in the Fast Flux Test Facility (FFTF).</p>	
5. <u>ON THE USE OF ISOTOPIC AND SPECTRAL TAILORING TO SIMULATE FUSION IRRADIATION VARIABLES IN FISSION REACTORS (U. of California, Santa Barbara)</u>	23
<p>It is shown that by using various isotopic ratios of $^{58}\text{Ni}/^{60}\text{Ni}$, single variable experiments on the effect of helium to displacement-per-atom ratios (Heldpa) can be carried out in ferritic and austenitic alloys. Further, additions of small amounts of ^{59}Ni result in the elimination of the low fluence transient, resulting in an approximately constant Heldpa ratio in the range up to 100 dpa.</p>	
6. <u>HELIUM PRODUCTION CROSS SECTIONS FOR 14.8-MeV NEUTRONS (RI)</u>	34
<p>Total helium production cross sections were measured for eleven separate isotopes of lead and tin irradiated in the 14.8-MeV T(d,n) neutron environment of RTNS-II.</p>	

CONTENTS (Cont'd)

7.	<u>HELIUM PRODUCTION IN REACTOR-IRRADIATED COPPER (RI)</u>	37
	The high measured helium concentrations (up to 81 appm) in copper irradiated in HFIR provide further evidence for the recently identified thermal three-stage reaction process.	
CHAPTER 3: REDUCED ACTIVATION MATERIALS		40
1.	<u>NEUTRON-INDUCED SWELLING OF Fe-Cr-Mn TERNARY ALLOYS (HEDL)</u>	41
	The swelling of Fe-Cr-Mn alloys is insensitive to irradiation temperature (420-600°C); the slight dependence on manganese content is thought to be the consequence of a composition-dependent densification, possibly associated with radiation-induced spinodal decomposition in the Fe-Cr-Mn Invar regime.	
2.	<u>FUNDAMENTAL IRRADIATION STUDIES ON VANADIUM ALLOYS (ANL, HEDL)</u>	46
	A joint DAFS/BES experiment on simple vanadium alloys is expected to be irradiated (in lithium) in FFTF-MOTA Cycles 7 and 8.	
CHAPTER 4: FUNDAMENTAL MECHANICAL BEHAVIOR		49
1.	<u>YIELD STRESS DETERMINATION FROM MINIATURIZED DISK BEND TEST DATA (MIT)</u>	50
	Yield stress has been successfully extracted from disk bend tests of a number of known materials using finite element simulation; simulation of the entire load/deflection curve up to fracture of the specimen has not yet been achieved.	
CHAPTER 5: RADIATION EFFECTS MECHANISMS AND CORRELATIONS		55
1.	<u>THE INFLUENCE OF THERMAL ANNEALING ON THE MICROSTRUCTURAL EVOLUTION IN HT-9 FERRITIC STEEL (U. Wisconsin-Madison)</u>	56
	HT-9 specimens annealed at temperatures between 300 and 900°C for 2 hrs or 24 hrs are microstructurally characterized.	
2.	<u>THE IDENTIFICATION OF CHI PHASE IN HEAVY ION IRRADIATED HT-9 FERRITIC STEEL (U. of Wisconsin-Madison)</u>	68
	HT-9 specimens irradiated at 500°C to 100 dpa with 14 MeV Ni ions exhibit the radiation-induced Chi phase.	
3.	<u>APPLICATION OF HIGH FLUENCE FAST REACTOR DATA TO FUSION-RELEVANT MATERIALS PROBLEMS (HEDL)</u>	73
	In three recent comparative studies in HFIR and EBR-II it was found that helium and solid transmutants produced no significant perturbation of the macroscopic property change under consideration.	
4.	<u>EFFECTS OF TENSILE AND COMPRESSIVE STRESSES ON IRRADIATION-INDUCED SWELLING IN AISI 316 (GE, HEDL)</u>	83
	Two recent experiments indicate that compressive stresses do not delay swelling as previously modeled but actually accelerate swelling at a rate comparable to that induced by tensile stresses.	

CONTENTS (Cont'd)

5.	<u>EARLY DEVELOPMENT OF SPINODAL DECOMPOSITION IN NEUTRON-IRRADIATED Fe-35Ni-7.5Cr AT 550°C (HEDL)</u>	92
	In Fe-35Ni-7.5Cr irradiated at 550°C to $2.5 \times 10^{22} \text{ n/cm}^2$ ($E > 0.1 \text{ MeV}$), the spinodal decomposition observed at higher irradiation temperatures and higher neutron exposures is just beginning to form.	
6.	<u>QWR/RTNS-II LOW EXPOSURE SPECTRAL EFFECTS EXPERIMENT (HEDL)</u>	99
	The first leg of the RTNS-II portion of this experiment was completed at a peak fluence of $2.4 \times 10^{18} \text{ n/cm}^2$. An excellent fit to the dosimetry data has been obtained.	
7.	<u>RADIATION-INDUCED PRECIPITATION IN Ti-64 (U. of Wisconsin-Madison)</u>	102
	The alloy Ti-64 was irradiated with 9-MeV Al ion to 2 dpa at 500-700°C. The density of the radiation-induced β precipitate decreased at high temperature while the size increased. The total fraction of bcc phase present is drastically altered by irradiation.	
8.	<u>HEAVY ION IRRADIATION OF Ti-6242s (U. of Wisconsin-Madison)</u>	117
	After 2 dpa of 9-MeV Al ion irradiation, Ti-6242s displayed extensive precipitation of a bcc phase at all temperatures in the range 450-700°C. The morphology below 600°C was highly unusual; it consisted of the apparent agglomeration of small (~20 nm) precipitates into some form of array or cluster.	
9.	<u>THE EFFECT OF DENSITY CHANGES ON THE ENERGY AND ION DEPOSITION PROFILES (U. of Wisconsin-Madison)</u>	130
	Using transport theory to calculate the distribution of deposited energy or deposited ions, it is shown that the effect of density changes on these distribution profiles can be obtained in a medium with constant density by a simple coordinate transformation, provided the distribution functions depend only on <u>one</u> spatial coordinate.	
10.	<u>STABILITY OF VACANCY CLUSTERS IN COPPER AND OTHER METALS (U. of Wisconsin-Madison)</u>	134
	The energies of voids, stacking fault tetrahedra and vacancy loops in aluminum, copper, nickel and stainless steel have been determined as a function of size using established equations from elasticity theory. Stacking fault tetrahedra and vacancy loops are the most stable small cluster morphologies in the absence of gas. Small amounts of oxygen or helium cause the void to be the most stable.	
11.	<u>A NOTE ON REACTIVE GAS CHARGING DURING PRE-IRRADIATION SPECIMEN PREPARATION (U. of Wisconsin-Madison)</u>	148
	The common misconception of hydrogen introduction during the pre-irradiation specimen electropolish has been addressed. It is shown that hydrogen cannot enter the specimen, but that the ingress of oxygen may occur during the electropolishing step. Hydrogen can, however, enter the specimen in the absence of the applied voltage if the sample, without a passive film layer, remains in the electrolyte.	
CHAPTER 6:	FUNDAMENTAL STUDIES OF SPECIAL PURPOSE MATERIALS	151
1.	<u>RADIATION-ENHANCED RECRYSTALLIZATION IN COPPER ALLOYS (U. of Wisconsin-Madison)</u>	152
	AMZIRC and AMAX-MZC exhibit signs of radiation-enhanced recrystallization following ion irradiation to 10 dpa at temperatures above 300°C. A simplified analysis suggests that the accelerated recrystallization kinetics is due to radiation-enhanced diffusion.	