


DOE/ER-0046/23

STOLLER



Damage Analysis and Fundamental Studies

Quarterly Progress Report
July-September 1985

November 1985

U.S. Department of Energy
Office of Energy Research
Office of Fusion Energy
Washington, DC 20545
B&R NO. AT-1502-03-04

CONTENTS

	Page
Foreword	iii
CHAPTER 1: IRRADIATION TEST FACILITIES	1
1. <u>RTNS-II IRRADIATIONS AND OPERATIONS (LLNL)</u>	2
<p>Irradiations were performed on seven different experiments during this quarter. The Japanese furnace was installed in the right target room.</p>	
CHAPTER 2: DOSIMETRY AND DAMAGE PARAMETERS	4
1. <u>DOSIMETRY MEASUREMENTS FOR THE ORR-6J PROTOTYPE EXPERIMENT (ANL)</u>	5
<p>Results are reported for a test of the 6J Japanese experiment in the Oak Ridge Research Reactor. Maximum fast fluxes above 0.1 MeV were 2.0×10^{14} n/cm²-s producing about 4.5 dpa per year in 316 stainless steel.</p>	
2. <u>HAFNIUM SHIELDING TESTS IN HFIR-RB POSITIONS AND REANALYSIS OF THE HFIR-RB1, RB2 EXPERIMENTS (ANL)</u>	9
<p>Analysis has been completed for the hafnium shield tests in the removable beryllium positions of the High Flux Isotopes Reactor (ORNL). The shield reduces the thermal flux by 90%, the epithermal flux by 50%, and the fast flux by only 5%. Yearly helium production in 316 stainless steel is thus reduced by a factor of 26 with little effect on displacement damage production. These new spectral analyses have been used to reanalyze previously reported results from the RB1 and RB2 materials irradiations in HFIR; the damage rates have been increased by 20-30%.</p>	
3. <u>SPECTRAL ANALYSIS FOR THE REAL84 PROJECT (ANL)</u>	16
<p>Results of our spectral analyses for seven different neutron fields have been submitted to the REAL84 Project, an international intercomparison of neutron spectral adjustment procedures and damage calculations. Our results will be compared with those from about 20 different laboratories by the International Atomic Energy Agency in Vienna.</p>	
CHAPTER 3: REDUCED ACTIVATION MATERIALS	17
1. <u>NEUTRON-INDUCED SWELLING AND MICROSTRUCTURAL DEVELOPMENT OF SIMPLE Fe-Mn AND Fe-Cr-Mn ALLOYS IN FFTF (HEDL)</u>	18
<p>Three Fe-Hn binary and six Fe-Mn-Cr ternary alloys have been irradiated in FFTF at temperatures of 420, 500 and 600°C to exposures ranging from 9-14 dpa. In contrast to the behavior of Fe-Cr-Ni alloys irradiated under comparable conditions there is essentially no dependence of void swelling on chromium or manganese content, and there also appears to be no dependence on irradiation temperature. Like Fe-Cr-Ni alloys, however, Fe-Cr-Mn and Fe-Mn alloys do swell at 1%/dpa after the transient regime.</p>	