



Damage Analysis and Fundamental Studies

Quarterly Progress Report
April-June 1985

August 1985

U.S. Department of Energy
Office of Energy Research
Office of Fusion Energy
Washington, DC 20545
B&R No. AT-15-O2-03-04

CONTENTS

	<u>Page</u>
Foreword	iii
CHAPTER 1: IRRADIATION TEST FACILITIES	1
1. <u>RTNS-II IRRADIATIONS AND OPERATIONS (LLNL)</u>	2
<p>Irradiations were performed on 18 different experiments during this quarter. Several machine improvements were made. David Short was appointed Manager of the RTNS-II effective May 9, 1985, and Dale Heikkinen was appointed Deputy Manager.</p>	
CHAPTER 2: DOSIMETRY AND DAMAGE PARAMETERS	4
1. <u>FISSION REACTOR DOSIMETRY - HFIR-RB2 (ANL)</u>	5
<p>Dosimetry measurements and damage calculations were completed for the RB2 experiment in the removable beryllium position in HFIR. The maximum neutron fluence was $6.50 \times 10^{22} \text{ n/cm}^2$ ($1.05 \times 10^{22} \text{ n/cm}^2$ above 0.1 MeV) resulting in 11 dpa and 1450 appm helium in 316 stainless steel.</p>	
2. <u>HELIUM PRODUCTION IN COPPER BY A THERMAL THREE-STAGE REACTION (RI, ANL)</u>	8
<p>Cross sections have been deduced for four reactions that allow one to calculate total helium production in copper for high-fluence irradiations in HFIR.</p>	
3. <u>ON ISOTOPIC ALLOYING TO TAILOR HELIUM PRODUCTION RATES IN MIXED SPECTRUM REACTORS (ORNL)</u>	13
<p>Isotopic alloying is examined as a means of manipulating the ratio of helium transmutations to atom displacements in mixed spectrum reactors. It is based on artificially altering the relative abundances of the stable isotopes of nickel to systematically vary the fraction of ^{58}Ni in nickel-bearing alloys.</p>	
CHAPTER 3: REDUCED ACTIVATION MATERIALS	24
1. <u>ACTIVATION CALCULATIONS WITH AN EXPANDED CROSS-SECTION LIBRARY (HEOL)</u>	25
<p>The activation of a number of elements has been calculated for 10 and 40 MW-y/m² exposures at a STARFIRE first wall location using a greatly expanded cross-section library and multiple time steps. The activation of critical radioisotopes increases nearly linearly with fluence.</p>	
CHAPTER 4: RADIATION EFFECTS MECHANISMS AND CORRELATIONS	29
1. <u>THE MICROSTRUCTURAL EVOLUTION OF HEAVY-ION-IRRADIATED HT-9 FERRITIC STEEL EXAMINED IN CROSS SECTION (U. Wisconsin-Madison)</u>	30
<p>HT-9 specimens were irradiated with 14-MeV Ni^{+3} ions to 200 dpa in the temperature range 300°C to 600°C and examined using a newly developed cross-section technique. Major features were dense dislocation loops at 300-400°C, chi-phase precipitates at 500°C, and the absence of significant damage at 600°C.</p>	
2. <u>EFFECTS OF CAVITATION ON DAMAGE CALCULATIONS IN ION-IRRADIATED P7 ALLOYS (U. of Wisconsin-Madison)</u>	39
<p>The depth-dependent void parameters extracted in cross section were used to model the effect of voids on the depth-dependent damage produced during 14-MeV nickel ion irradiation of alloy P7 (essentially high purity 316 stainless steel). Corrections applied to the dose at the peak swelling depth yield swelling rates approaching 0.7%/dpa.</p>	