



Damage Analysis and Fundamental Studies

Quarterly Progress Report
April-June, 1979

July 1979

**U.S. Department of Energy
Assistant Secretary for Energy Technology
Office of Fusion Energy**

CONTENTS

	<u>Page</u>
Foreword	iii
Figures	xv
Tables	xxiii
CHAPTER 1. DAFS TASK GROUP ACTIVITIES	1
 <i>A Subtask Group meeting on damage production calculations and models was held at Livermore on June 7-8.</i>	
 <i>Procurement has begun of DAFS specimen materials.</i>	
CHAPTER 2. IRRADIATION TEST FACILITIES	5
1. <u>RTNS-II Operations</u> (LLL)	7
 <i>A deuteron beam diagnostics system has been installed in order to improve neutron utilization. Irradiation, dosimetry and handling services are routinely being provided for user laboratories.</i>	
CHAPTER 3. SUBTASK A: ENVIRONMENTAL CHARACTERIZATION	11
1. <u>Experiments at the Oak Ridge Research Reactor</u> (ANL)	13
 <i>Flux-spectral measurements in core position E7 of the Oak Ridge Research Reactor are summarized; the fraction of neutrons below 1 MeV is less than indicated by neutronic calculations. The analysis of ORR-MFE1 dosimetry is nearly completed.</i>	

CONTENTS (Cont'd)

	<u>Page</u>
2. <u>Helium Accumulation Fluence Dosimetry for the MFE Spectral Characterization and MFE-1 Irradiations at the Oak Ridge Research Reactor (RI)</u>	21
<i>Preliminary helium analysis results are given for selected helium accumulation dosimetry samples irradiated in the MFE spectral characterization and MFE-1 experiments in the Oak Ridge Research Reactor.</i>	
3. <u>Dosimetry at the IPNS Spallation Source (ANL)</u>	27
<i>Neutron and proton flux-spectral measurements have been completed at a mock-up of the Intense Pulsed Neutron Source (IPNS) at the Zero Gradient Synchrotron at Argonne. Neutrons were produced by spallation from a 500 MeV proton beam stopped in Ta and U targets.</i>	
4. <u>Revision and Application of the STAYSL Computer Code (ANL)</u>	29
<i>The computer code STAYSL by F. G. Perey (ORNL) is now operational at Argonne. This code uses a variance-covariance technique to determine a neutron flux-spectrum from foil activation measurements; it is now being compared with our Monte Carlo unfolding code SANDANL.</i>	

CONTENTS (Cont'd)

	<u>Page</u>
5A. <u>High Energy Neutron Cross Sections for Transport and Damage Calculations</u> (HEDL)	33
<i>The evaluation of 20 to 60 MeV neutron cross sections for neutron transport and damage calculations is described.</i>	
5B. <u>Deuteron and Neutron Induced Activation of FMIT Accelerator and Beam Transport Structural Materials</u> (HEDL)	35
<i>Calculations of deuteron and neutron induced activation of FMIT structural materials identify Fe and Co as the largest contributors for all irradiation and cooling times examined.</i>	
5C. <u>Deuteron and Neutron Induced Activation of the Lithium Target</u> (HEDL)	36
<i>A preliminary measurement of deuteron-induced production of ^7Be, one of the most troublesome radioactinants in the FMIT lithium target system, gave a higher yield than anticipated.</i>	
6A. <u>Cross Section Prediction</u> (HEDL)	40
<i>The few parameters in the model for angular distributions of outgoing particles can be expressed as functions of ℓ, the order of the Legendre polynomial.</i>	

CONTENTS (Cont'd)

	<u>Page</u>
6B. <u>Neutron Yield Experiments</u> (HEDL)	40
<i>Results of measurements of the yield and spectra of neutrons from 35 MeV deuterons on thick targets of both natural lithium and ^6Li are described.</i>	
6C. <u>Microscopic Neutron Yield Model</u> (HEDL)	43
<i>The microscopic neutron yield model is being updated using HEDL-UCD experimental results, least-squares adjustment techniques and nuclear models.</i>	
7A. <u>Use of the Magnetic Fusion Energy Computer Center</u> (BNL)	45
<i>Transfer of damage analysis calculations to the MFECC is progressing.</i>	
7B. <u>Cross Sections for Atomic Displacements by Gamma Rays</u> (BNL)	45
<i>The displacement cross sections for both gamma rays and neutrons have been evaluated for Al_2O_3.</i>	

CONTENTS (Cont'd)

	<u>Page</u>
CHAPTER 4. SUBTASK B: DAMAGE PRODUCTION	55
1. <u>Functions Describing Disordering Replacements and Secondary Displacements in Collision Cascades in Polyatomic Materials</u> (LASL)	57
<i>Calculations for Nb₃Sn show that the atom type that produces the majority of secondary displacements is a strong function of PKA type and energy.</i>	
2. <u>Documentation of COMENT</u> (HEDL)	67
<i>A draft of a document describing the dynamical computer code COMENT has been completed.</i>	
3. <u>A Comparison of Experimental Defect Production Efficiency in Molybdenum with Computer Simulation in Tungsten</u> (LLL)	71
<i>Fully dynamic computer simulations of defect production as a function of primary recoil energy in tungsten are in close agreement with experimental results for molybdenum. The decreased production efficiency for recoils above a few keV is the result of additional recombination occurring in the highly agitated lattice.</i>	
4. <u>The Anisotropy of Defect Production in Tungsten</u> (LLL)	79
<i>Calculations of the anisotropy of the displacement threshold in tungsten compare favorably with experiments on molybdenum and tungsten. Thresholds near <111> and <110> are, respectively, 1.2 and 2.3 times the minimum threshold in the <100> direction.</i>	

CONTENTS (Cont'd)

		<u>Page</u>
5A.	<u>RTNS-II Irradiation Program (HEDL)</u>	84
	<i>Two ambient temperature irradiations at RTNS-II have been completed to estimated fluences of 3×10^{17} n/cm² and 1×10^{18} n/cm². Specimens were TEM disks of pure metals, Fe-Ni-Cr, Fe-Ni-Cr-Mo, and representative alloy development program materials.</i>	
5B.	<u>RTNS-II Furnace Development (HEDL)</u>	88
	<i>Construction of a high temperature, ultra high vacuum furnace for general use at RTNS-II has been completed.</i>	
5C.	<u>LPTR Furnace Development (HEDL)</u>	88
	<i>A furnace to be used in the Livermore Pool-Type Reactor (LPTR) is being designed at LLL as a joint LLL-HEDL project.</i>	
 CHAPTER 5. SUBTASK C: DAMAGE MICROSTRUCTURE EVOLUTION AND MECHANICAL BEHAVIOR		
1.	<u>Oxide Dispersoid Stability in Irradiated Alloys (MIT)</u>	94
	<i>The stability of incoherent oxide dispersoids may be significantly altered by MFR first wall irradiation conditions; evaluation must be on a case by case basis.</i>	

CONTENTS (Cont'd)

	<u>Page</u>
2. <u>Void Nucleation at Heterogeneities</u> (MIT)	104
<i>Dislocations and interfaces are potential void nucleation sites only when not point defect sinks; in the presence of inert gas, they are excellent catalysts.</i>	
3A. <u>Effect of Time/Temperature History of Helium Doping and Atomic Displacement Damage on Microstructural Evolution in 20% Cold Worked 316 SS (MFE Heat)</u> (W-R&D)	119
<i>By varying the helium implantation and atomic displacement rates independently, it is found that the instantaneous helium implantation rate is an important factor in cavity formation.</i>	
3B. <u>Microstructural Effects of Dual-Ion Bombardment in Aged 316 SS</u> (W-R&D)	123
<i>Bombardment of 316 SS, aged at 800°C to produce large grain boundary carbides prior to dual-ion irradiation, results in large cavities at the carbide/austenite interfaces for bombardment temperatures above 650°C.</i>	
3C. <u>Damage Rate Dependence of the Rapid Cavity Growth Rate Regime in Solution Annealed 316 SS</u> (W-R&D)	128
<i>The rapid cavity growth regime observed in solution annealed 316 SS under dual-ion bombardment at 600°C is shown to occur only for atomic displacement rates below $\sim 1.5 \times 10^{-4}$ dpa/s for helium injection rates of 2×10^{-4} appm/s to 3×10^{-3} appm/s.</i>	

CONTENTS (Cont'd)

		<u>Page</u>
3D.	<u>Numerical Analysis of Cavity Size Distributions</u> (W-R&D)	134
	<i>A computerized data file permitting conjunctive queries and parametric analysis of dual-ion irradiation data has been constructed.</i>	
4.	<u>Boron Doping of Stainless Steel by Rapid Quenching</u> (MIT)	141
	<i>Splat quenched stainless steel ribbons containing 5000 appm B, and 5000 appm B and 5000 appm Zr were prepared using the melt spinning technique.</i>	
5.	<u>The Radiation Disorder Model of Phase Stability</u> (University of Wisconsin)	144
	<i>A new theoretical approach to radiation disordering is developed and applied to radiation-induced phase instability.</i>	
6.	<u>Correlation of 16 MeV Protons with Fusion Neutrons</u> (PNL)	186
	<i>Sixteen MeV protons induced 1.6 times more hardening in niobium than Be(d,n) neutrons in the first hardening stage while hardening rates were equal in the higher fluence stage. The hardening rate of T(d,n), Be(d,n) and 16 MeV proton irradiated nickel can be described by a single relationship as a function of fluence.</i>	

CONTENTS (Cont'd)

	<u>Page</u>
7. <u>Effect of Temperature and Microstructure on Crack Propagation in Unirradiated and Irradiated Austenitic Stainless Steel (University of Virginia)</u>	193
<i>The nature of crack propagation observed in in-situ HVEM tensile tests of 304 and 316 stainless steels can be correlated with the nature of the failure mode.</i>	
8. <u>Effects of Near Surface Damage and Helium on the Performance of the First Wall (MIT)</u>	209
<i>The in-core cycling system functions as expected, with a cycle time of four minutes. Safety related out-of-core experiments show that specimen wall thickness could be increased.</i>	
9. <u>Leak Rate Fatigue Experiment (PNL)</u>	218
<i>Thin unirradiated 304 SS tubes have been cycled at 500°C at maximum tangential stresses ranging from 224 MPa to 348 MPa. No indication of a leak was observed in 10⁴ cycles at stresses below 286 MPa while at higher stresses the majority of failures were due to rupture.</i>	
10. <u>Radiation Induced Segregation and Irradiation Creep (ANL)</u>	226
<i>Irradiations of Ni and Ni - 4 at.% Si with 21 MeV deuterons at 2×10^{-6} dpa · s⁻¹ to ~0.08 dpa showed greater radiation induced creep in Ni; hardening was observed only in the alloy.</i>	